## LANKA TILES PLC

CE [SIS]

## LANKA TILES PLC

215, Nwala Road, Narahenpita, Colombo 05, Sri Lanka. Tel: +94-11-2808050 Fax: +94-11-2806232 Email: <u>info@lankatiles.com</u> Website: <u>www.lankatiles.com</u> Factory: St.James Estate, Jaltara, Ranala. Tel: +94 11 2141055 Fax: +94 11 2141045 Co. Reg. No. PQ129

## **TECHNICAL SPECIFICATION**

Glazed Porcelain Floor Tiles produced by LANKA TILES PLC comply with ISO 13006:2018(E) Annex H, BS EN 14411:2012 Annex H,SLS 1181:2019 standards.Series: AmbekkeTheme: HeritageColour: Brown

Tile Type: FAY-AMB---M0086A56 Tile Size: 600x600 mm Tile Surface: Matt **DIMENSIONS & SURFACE QUALITY** GLAZE PORCELAIN IMAGE Test methods TEST BS EN ISO Annex H STATUS Group B 1b Length & width ISO 10545-2 +/-0.3% 1/// Thickness ISO 10545-2 +/-5.0% Straightness of sides ISO 10545-2 +/-0.5%Centre curvature ISO 10545-2 +/-0.5% ISO 10545-2 Edge curvature +/-0.5% Comply Warpage ISO 10545-2 +/-0.5% ISO 10545-2 Rectangularity +/-0.5% ISO 10545-2 Minimum of 95 % of tiles shall be free Surface quality from visible defects that would impair the appearance of a major area of tiles. PHYSICAL PROPERTIES ISO 10545-3 Water absorption  $0.5~\% < E \leq 3~\%$ Individual max 3.3% ISO 10545-4 Not less than 1100 N Breaking strength Comply (Thickness  $\geq$  7.5mm) Min 30 N/ mm<sup>2</sup> Modulus of rupture ŧ ISO 10545-4 Individual min 27 N/mm<sup>2</sup> Resistance to surface abrasion-glazed tiles ISO 10545-7 Reported abrasion class and cycle passed Class 3 ABRASION Resistance to Thermal shock ISO 10545-9 Required I: Comply Resistance to crazing-glazed tiles ISO 10545-11 Required 4 CHEMICAL PROPERTIES Resistance to staining ISO 10545-14 Minimum class 3 Class 4 STAIN Resistance to low concentrations of acids ISO 10545-13 Manufacturer to state classification Class GLA CHEMICAL Resistance to low concentrations of alkalis ISO 10545-13 Manufacturer to state classification Class GLA 5 CHEMICAL ISO 10545-13 Minimum GB Resistance to household chemicals and swimming pool salts GA Phases of Design Multiple Faces ✓ Single Face Random Faces APPLICATIONS Recommended for industrial, residential, or medium traffic commercial floor covering areas (indoor/outdoor) subject to normal footwear. Ex- Office area except entrances, Kitchens, Corridors and balconies, Laboratories which are not \* required strong acid resistance. Cleaning ability to be considered.

Last Update: 2024-10-01

Prepared By : Executive (QA)

Approved By : Manager (QA/RD)



ISO ISO