LANKA TILES PLC FO/QA/64

## **LANKA TILES PLC**

215, Nwala Road, Narahenpita, Colombo 05, Sri Lanka.

Tel: +94-11-2808050 Fax: +94-11-2806232

Email: info@lankatiles.com Website: www.lankatiles.com

Factory: St.James Estate, Jaltara, Ranala. Tel: +94 11 2141055 Fax: +94 11 2141045

Co. Reg. No. PQ129

## LANKATILES

Fine Living Redefined









## TECHNICAL SPECIFICATION

Glazed Porcelain Floor Tiles produced by LANKA TILES PLC comply with ISO 13006:2018(E) Annex H, BS EN 14411:2012 Annex H, SLS 1181:2019 standards.

Series: Roden Theme: Mountain Colour: Beige
Tile Type: FAY-RDN---X0138A56 Tile Size: 600x600 mm Tile Surface: Matt

| DIMENSIONS & SURFACE QUALITY                              | IMAGE                 | Test methods<br>BS EN ISO   | GLAZE PORCELAIN Annex H Group B 1b   | TEST<br>STATUS |
|---|-----------------------|---|--|----------------|
| Length & width  | 11/1/1                | ISO 10545-2   | +/-0.3%  | Comply         |
| Thickness   |                       | ISO 10545-2   | +/-5.0%  |                |
| Straightness of sides                                     |                       | ISO 10545-2   | +/-0.5%  |                |
| Centre curvature  |                       | ISO 10545-2   | +/-0.5%  |                |
| Edge curvature  | $\Diamond$            | ISO 10545-2   | +/-0.5%  |                |
| Warpage   | \\                    | ISO 10545-2   | +/-0.5%  |                |
| Rectangularity  |                       | ISO 10545-2   | +/-0.5%  |                |
| Surface quality   |                       | ISO 10545-2   | Minimum of 95 % of tiles shall be free from visible defects that would impair the appearance of a major area of tiles. |                |
| PHYSICAL PROPERTIES                                       |                       |   |  |                |
| Water absorption  |                       | ISO 10545-3   | $0.5~\% < E \le 3~\%$ Individual max 3.3%  | Comply         |
| Breaking strength   |                       | ISO 10545-4   | Not less than 1100 N<br>(Thickness ≥ 7.5mm)  |                |
| Modulus of rupture  |                       | ISO 10545-4   | Min 30 N/ mm <sup>2</sup><br>Individual min 27 N/mm <sup>2</sup>   |                |
| Resistance to surface abrasion-glazed tiles               | ABRASION<br>RESISTANT | ISO 10545-7   | Reported abrasion class and cycle passed   | Class 3        |
| Resistance to Thermal shock                               | I.                    | ISO 10545-9   | Required   | ply            |
| Resistance to crazing-glazed tiles                        | 9                     | ISO 10545-11  | Required   | Comply         |
| CHEMICAL PROPERTIES                                       |                       | •   |  |                |
| Resistance to staining                                    | STAIN<br>RESISTANT    | ISO 10545-14  | Minimum class 3  | Class 4        |
| Resistance to low concentrations of acids                 | CHEMICAL RESISTANT    | ISO 10545-13  | Manufacturer to state classification   | Class GLA      |
| Resistance to low concentrations of alkalis               | CHEMICAL<br>RESISTANT | ISO 10545-13  | Manufacturer to state classification   | Class GLA      |
| Resistance to household chemicals and swimming pool salts | CHEMICAL              | ISO 10545-13  | Minimum GB   | GA             |
| Phases of Design  |                       | ☐ Single Face ☐ Multiple Faces ☑ Random Faces   |  |                |
| APPLICATIONS  | * *                   | Recommended for industrial, residential, or medium traffic commercial floor covering areas (indoor/outdoor) subject to normal footwear. Ex- Office area except entrances, Kitchens, Corridors and balconies, Laboratories which are not required strong acid resistance. Cleaning ability to be considered. |  |                |

Last Update: 2024-10-01 Prepared By : Executive (QA) Approved By : Manager (QA/RD)

Issue No: 1 Revision No: 0 Date: 2024-10-01